



# HITEX INSULATION (NINGBO) CO., LTD

Room2004,2<sup>nd</sup> Block, Shangdong Business Centre, Ningbo,315043

Tel:+86-574-27898220,Fax:+86-574-27898230

## مشخصات فنی پارچه سیلیکا 240 گرمی

|                   |   |                                     |                    |
|-------------------|---|-------------------------------------|--------------------|
| Name              | Silica Cloth  | Style                               | SILICA260-0.82-100 |
| Date              | 2012-3-15   | Test Date                           | 2012-3-20          |
| Test Index & Item |   |                                     |                    |
| Sril.             | Item  | Standard                            |                    |
| 1                 | PRODUCT CODE  | SILICA240                           |                    |
| 2                 | WIDTH, cm   | 82 ±2                               |                    |
| 3                 | WEAVE STYLE   | PLAIN                               |                    |
| 4                 | WARP YARN   | JC9 33X1X2                          |                    |
| 5                 | FILL YARN   | JC9 33X1X2                          |                    |
| 6                 | WARP COUNTS, ends/inch                                | 40±2                                |                    |
| 7                 | FILL COUNTS, ends/inch                                | 30±2                                |                    |
| 8                 | MD BRK STRN,<br>1bs/1x4 inch                          | ≥150                                |                    |
| 9                 | CD BRK STRN,<br>1bs/1x4 inch                          | ≥110                                |                    |
| 10                | WEIGHT g/m <sup>2</sup>                               | 240±20                              |                    |
| 11                | STD ROLL, M/roll                                      | 100                                 |                    |
| 12                | THICKNESS, mm   | 0.25                                |                    |
| 13                | SiO <sub>2</sub> CONTENT %                            | ≥96                                 |                    |
| 14                | LINEAR HOT STRAINING<br>COEFFICIENT OF<br>CONTRACTION | ≤6%(980°C after 30min)              |                    |
| 15                | TEMPERATURE   | <982°C (1800°F)<br>environment only |                    |
| 16                | ACID AND ALKALI RESISTAMCE                            | Acid resistance only                |                    |

All information data quoted are based on our extensive tests and years of experience, however, they can only serve as guide value. Failure to select proper sealing products could result in properly damage and/or serious injury. Specifications are subject to change without notice.